






Modern Vintage & Modern Vintage Chic - Datasheet

		Standard requirement	Test result										
Product specifications			Pass										
Total thickness	EN ISO 24346	2.5 mm	✓	-									
Thickness of wear layer	EN ISO 24340	0.55 mm	✓	-									
Weight	EN ISO 23997	4,400 g/m ²	✓	-									
Side length, delivery form	EN ISO 24342	-	✓	<table style="font-size: small; border-collapse: collapse;"> <tr> <td></td> <td style="text-align: center;">Modern Vintage</td> <td style="text-align: center;">Modern Vintage Chic</td> </tr> <tr> <td>Size</td> <td style="text-align: center;">304.8 x 76.2 mm</td> <td style="text-align: center;">720 x 144 mm</td> </tr> <tr> <td>Carton</td> <td style="text-align: center;">144 planks = 3.34 m²</td> <td style="text-align: center;">32 planks = 3.32 m²</td> </tr> </table>		Modern Vintage	Modern Vintage Chic	Size	304.8 x 76.2 mm	720 x 144 mm	Carton	144 planks = 3.34 m ²	32 planks = 3.32 m ²
	Modern Vintage	Modern Vintage Chic											
Size	304.8 x 76.2 mm	720 x 144 mm											
Carton	144 planks = 3.34 m ²	32 planks = 3.32 m ²											
Classification & Certification													
Type of flooring	EN ISO 10582	Heterogeneous, PVC	✓	-									
Classification	EN ISO 10874	22/33/42 , 31/34/43	✓	-									
Burning behaviour	EN 13501-1/ EN ISO 9239-1/ 11925-2 EN 14041: 2004/AC:2006	Bfl-s1	✓	Bfl-s1 									
Slip resistance	DIN 51130/ EN 13893 EN 14041: 2004/AC:2006	R9, DS	✓	R10, DS 									
Declaration of Performance	-	-	-	No. GFL GD – DoP - 018									
Technical properties													
Abrasion resistance	EN ISO 10582	-	✓	Class T									
Dimension stability	EN ISO 23999	< 0.25%	✓	< 0.05 %									
Squareness & straightness	EN ISO 24342	< 0.35 mm tolerance	✓	< 0.20 mm									
Curling after exposure to heat	EN ISO 23999	< 2 mm	✓	0 mm									
Residual indentation	EN ISO 24343-1	< 0.1 mm	✓	0.05 mm									
Castor wheel chair	ISO 4918	25,000 revolutions	✓	suitable, type W									
Flexibility	EN ISO 24344	20 mm no crack	✓	< 10 mm no crack									
Surface treatment	-	-	-	Top Protection Plus, PUR									
Color fastness	EN ISO 105-B02	≥ 6	✓	> 6									
Staining & resistance to chemicals <small>Caucstic soda solution (25%), Citric acid (10%), Acetone, Coffee (120g/l)</small>	EN ISO 26987	-	✓	Index 0 , excellent									
Thermal resistance	EN ISO 8302	-	✓	0.019 m ² K/W									
Underfloor heating	-	-	✓	suitable, max. 27°C									
Environment / Indoor air quality													
Formaldehyde emissions	EN 14041: 2004/AC:2006	-	✓										
Pentachlorophenol content	EN 14041: 2004/AC:2006	-	✓										
TVOC after 28 days	ISO 16000	-	✓	certified A+ (ÖTI report No. 71745) 									
REACH	Regulation (EU) No. 1907/2006	in conformity	✓	no SVHC (Centexbel report No. 14.01560.02)									